

MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

1. Application

電介質材料 Dielectric Material	NPO COG	X7R	Z5U	Y5V
電介質種類 Dielectric Type	I 類電介質 Stable Class I		II 類電介質 Stable Class II Dielectric	
電氣性能 Electrical Properties	電氣性能最穩定，基本上不隨溫度、電壓和時間的改變而改變。 With negligible dependence of electrical properties on temperature, voltage, frequency and time.	電氣性能較穩定，在溫度、電壓與時間改變時性能的變化不明顯，由於X7R是一種強電介質，因而能造出容量比NPO電介質更大的電容器。 With predictable change of properties with temperature, voltage, frequency and time, this dielectric is ferroelectric and offers higher capacitance ranges than class I .		具有較高的介電常數，常用於生產比容較大、標稱容量較高的大容量電容器產品，但其容量穩定性能較X7R差，容量損耗對溫度、電壓等測試條件敏感。 With higher dielectric constant and greater variation of properties with temperature and test conditions, very high capacitance per unit volume and suited for bypass and coupling application as well as filtering, transient suppression blocking, and charge storage application.
應用 Application	適用於穩定性要求高的高頻電路，如溫度補償電路、震盪電路等。 Used in circuit requiring stable performance, such as temperature compensation circuits and smite circuits.	適用於隔直、偶合、旁路與對電容穩定性要求不太高的濾頻電路。 Used as blocking, coupling, By-passing and frequency discriminating elements.	適用於要求容量較大的電路，如儲能、記憶電路等。 Suited for By-passing and coupling application such as store power and memory circuit.	
使用溫度 Operating	-55°C ~+125 °C	-55 °C ~+125 °C	+10°C ~85°C	-30 °C ~+85 °C
溫度係數 Temperature	0 ± 30 ppm/°C	± 15%	+22%~-56%	+22%~-82%




MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE



2. How to order

AD15	Z	104	M	1H	1	R
SIZE	T.C.	CAPACITANCE	TOLERANCE	VOLTAGE	PACKAGE & QTY	PACKAGE
AD15	N=NPO	1PF = 1R0	J=±5%	1E=25V	1=10000 PCS/REEL	R= TAPE / REEL
AD20	B=X7R	1.5PF = 1R5	K=±10%	1H=50V	7=7500 PCS/REEL	B TAPE / BOX
	Z=Z5U	2.2PF =2R2	M=±20%	2A=100V	5=5000 PCS/BOX	(mm)
	Y=Y5V	100PF=101	Z=+80 ~ -20%	2D=200V	0=5000 PCS/REEL	
	X=X5R	120PF=121		2H=500V		
		10nF=103		2J=630V		
		100nF= 104		3A=1KV		
				3D=2KV		
				3F=3KV		

3. Construction



4. Size Code Dimension



CINETECH
SYMBOL OF QUALITY

MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

6. Marking

項目 Item	尺寸大小 Size Code	晶片大小 Chip Size	L Max.	D Max.	A Min.	G	S
T	A15	603	3.5	2.54	25.4	0.5±0.05	--
	A15	805	3.5	2.54	25.4	0.5±0.05	--
	A20	1206	5	3	25.4	0.5±0.05	--
B	A15	603	3.5	2.54	7±0.8	0.5±0.05	5±0.5
	A15	805	3.5	2.54	7±0.8	0.5±0.05	5±0.5
	A20	1206	5	3	7±0.8	0.5±0.05	7.5±0.5

6. Marking


顏色 Color	黑色 Black	
電容量 Capacitance	公差 Tolerance	印字 Marking
100	J	10 J
220	J	22 J
470	J	47 J
101	J	101
471	J/K	471
102	J/K	102
103	K/M	103
104	M/M/Z	104
105	K/M/Z	105



MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

7. Packing Specification



8. Packing Quantity

項目 Item	立式電容器 Radial Leaded	臥式電容器 Axial Leaded Type
編帶/捲裝 Tape & Reel	4000 pcs/捲 4000 pcs/Reel	7500 pcs/捲 7500 pcs/Reel
編帶/盒裝 Tape & Box	2000 pcs/盒 2000 pcs/Box	5000 pcs/盒 5000 pcs/Box
散裝 Bulk Pack	1000 pcs/包 1000 pcs/bag	1000 pcs/包 1000 pcs/bag

CINETECH
SYMBOL OF QUALITY

MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

9. Inspection Norm

檢驗項目 Item	檢驗標準Inspection Norm			
	NPO/COG	X7R	Z5U	Y5V
電容量 Capacitance	測試頻率： Test Frequency : $\leq 1000\text{PF}=1\text{Mhz}$ $> 1000\text{PF}=1\text{Khz}$	測試頻率： Test Frequency : 1Khz	測試頻率： Test Frequency : 1Khz	測試頻率： Test Frequency : 1Khz
	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$	測試電壓： Test Voltage: $0.5 \pm 0.1 \text{ Vrms}$	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$
	在允差範圍內： In the tolerance : $C=\pm 0.25\text{pf}$ $D=\pm 0.50\text{pf}$ $J=\pm 5\%$	在允差範圍內： In the tolerance : $J=\pm 5\%\text{pF}$ $K=\pm 10\%$ $M=\pm 20\%$	在允差範圍內： In the tolerance : $M=\pm 20\%$ $Z=+80\%/-20\%$	在允差範圍內： In the tolerance : $M=\pm 20\%$ $Z=+80\%/-20\%$
消散係數(DF) Dissipation Factor	測試頻率： Test Frequency : $\leq 1000\text{PF}=1\text{Mhz}$ $> 1000\text{PF}=1\text{Khz}$	測試頻率： Test Frequency : 1Khz	測試頻率： Test Frequency : 1Khz	測試頻率： Test Frequency : 1Khz
	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$ $< 0.1 \%$	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$ $< 2.5\%-100/50\text{V}$ $< 3.5\%-25/16\text{V}$	測試電壓： Test Voltage: $0.5 \pm 0.1 \text{ Vrms}$ $< 4.0 \%$	測試電壓： Test Voltage: $1 \pm 0.2 \text{ Vrms}$ $< 5.0\%-100/50\text{V}$ $< 7.0\%-25/16\text{V}$
絕緣組抗(IR) Insulation Resistance $500\Omega=C*R$ $500\Omega=0.47\text{UF} \cdot 1064\text{M}\Omega$	測試電壓：Test Voltage 額定電壓 :Rated Voltage	測試電壓：Test Voltage 額定電壓 :Rated Voltage	測試電壓 Test Voltage 額定電壓 :Rated Voltage	測試電壓 :Test Voltage 額定電壓 :Rated Voltage
	兩個中的最小值： Whichever is less $\geq 10 \text{ Gohmas}$ or $\geq 1000 \text{ M}\Omega$	兩個中的最小值： Whichever is less $\geq 10 \text{ Gohmas}$ or $\geq 1000 \text{ M}\Omega$	兩個中的最小值： Whichever is less $\geq 10 \text{ Gohmas}$ or $\geq 1000 \text{ M}\Omega$	兩個中的最小值： Whichever is less $\geq 10 \text{ Gohmas}$ or $\geq 1000 \text{ M}\Omega$
耐電壓(TV) Voltage	2.5倍額定電壓 $2.5 \times \text{rated Voltage}$	2.5倍額定電壓 $2.5 \times \text{rated Voltage}$	2.5倍額定電壓 $2.5 \times \text{rated}$	2.5倍額定電壓 $2.5 \times \text{rated Voltage}$



MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

10. Reliability


項目 (Item)	檢驗方法 (Test Methods)	檢驗標準 (Test Specifications)																																													
焊錫性 Solderability	將電容器導線浸入松香溶液後浸入焊錫槽溫度為 $235\pm 5^{\circ}\text{C}$ 的焊錫中5秒,浸入深度距離電容本體 2.5~3mm. The lead wire of a capacitor shall be dipped into a rosin and then into molten solder of $235\pm 5^{\circ}\text{C}$ for 5 seconds , in both cases the depth of dipping is up to about 2.5 to 3.0 mm from the root of lead wires.	導線表面均勻沾錫,上錫面積不小於總面積的75%。 Lead wire shall be soldered with uniformly coated on the Axial or Radial direction over 75% of the circumferential direction.																																													
耐焊性 Resistance to Soldering heat	焊錫溫度 $265\pm 5^{\circ}\text{C}$,時間 5 ± 0.5 秒, 插入深度距離電容本體2.5~3mm,試驗後 24 ± 2 小時測量。 The lead wire shall be immersed into the melted solder of $265\pm 5^{\circ}\text{C}$, up to about 2.5 to 3.0 mm from the main body and the specified items shall be measured after leaving for 24 ± 2 hours.	1.外觀 : 無損傷 Appearance : No marked defect 2.電容值變化($\Delta C/C$) : Capacitance change : <table border="1"> <thead> <tr> <th></th> <th>COG</th> <th>X7R</th> <th>Z5U</th> <th>Y5V</th> </tr> </thead> <tbody> <tr> <td>$\Delta C/C$</td> <td>$\leq \pm 0.5\%$, or $\pm 0.5\text{pf}$</td> <td>$\leq \pm 7.5\%$</td> <td>$\leq \pm 20\%$</td> <td>$\leq \pm 20\%$</td> </tr> </tbody> </table>		COG	X7R	Z5U	Y5V	$\Delta C/C$	$\leq \pm 0.5\%$, or $\pm 0.5\text{pf}$	$\leq \pm 7.5\%$	$\leq \pm 20\%$	$\leq \pm 20\%$																																			
	COG	X7R	Z5U	Y5V																																											
$\Delta C/C$	$\leq \pm 0.5\%$, or $\pm 0.5\text{pf}$	$\leq \pm 7.5\%$	$\leq \pm 20\%$	$\leq \pm 20\%$																																											
壽命實驗 Life Test	<table border="1"> <thead> <tr> <th>條件 Condition</th> <th>NPO</th> <th>X7R</th> <th>Z5U</th> <th>Y5V</th> </tr> </thead> <tbody> <tr> <td>溫度 Temperature</td> <td>$+125^{\circ}\text{C}$</td> <td>$+85^{\circ}\text{C}$</td> <td></td> <td></td> </tr> <tr> <td>時間 Time</td> <td colspan="4">1000 小時(hours)</td> </tr> <tr> <td>電壓 Voltage</td> <td colspan="4">1.5×額定電壓 (rated voltage applied)</td> </tr> <tr> <td>恢復時間 Recovery time</td> <td colspan="4">24± 2 小時(hours)</td> </tr> </tbody> </table>	條件 Condition	NPO	X7R	Z5U	Y5V	溫度 Temperature	$+125^{\circ}\text{C}$	$+85^{\circ}\text{C}$			時間 Time	1000 小時(hours)				電壓 Voltage	1.5×額定電壓 (rated voltage applied)				恢復時間 Recovery time	24 ± 2 小時(hours)				1.外觀 : 無損傷 Appearance : No marked defect 2.變化值 (Change value) : <table border="1"> <thead> <tr> <th></th> <th>COG</th> <th>X7R</th> <th>Z5U</th> <th>Y5V</th> </tr> </thead> <tbody> <tr> <td>$\Delta C/C$</td> <td>$\leq \pm 2\%$, or $\pm 2\text{pf}$</td> <td>$\leq \pm 10\%$</td> <td>$\leq \pm 20\%$</td> <td>$\leq \pm 30\%$</td> </tr> <tr> <td>DF</td> <td colspan="4">$\leq 1.5 \times \text{initial requirement}$</td> </tr> <tr> <td>IR</td> <td colspan="4">$\geq 0.25 \times \text{initial requirement}$</td> </tr> </tbody> </table>		COG	X7R	Z5U	Y5V	$\Delta C/C$	$\leq \pm 2\%$, or $\pm 2\text{pf}$	$\leq \pm 10\%$	$\leq \pm 20\%$	$\leq \pm 30\%$	DF	$\leq 1.5 \times \text{initial requirement}$				IR	$\geq 0.25 \times \text{initial requirement}$			
條件 Condition	NPO	X7R	Z5U	Y5V																																											
溫度 Temperature	$+125^{\circ}\text{C}$	$+85^{\circ}\text{C}$																																													
時間 Time	1000 小時(hours)																																														
電壓 Voltage	1.5×額定電壓 (rated voltage applied)																																														
恢復時間 Recovery time	24 ± 2 小時(hours)																																														
	COG	X7R	Z5U	Y5V																																											
$\Delta C/C$	$\leq \pm 2\%$, or $\pm 2\text{pf}$	$\leq \pm 10\%$	$\leq \pm 20\%$	$\leq \pm 30\%$																																											
DF	$\leq 1.5 \times \text{initial requirement}$																																														
IR	$\geq 0.25 \times \text{initial requirement}$																																														
引出端強度 Strength of lead	固定電容器並在兩端導線加力。 Fix the body of capacitor, apply a tensile weight gradually to each lead.	拉力 : 臥式電容器 : $> 4\text{kg}$ 立式電容器 : $> 1\text{ kg}$ Pull : Axial : $> 4\text{ kg}$ Radial : $> 1\text{ kg}$																																													



MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

11.Temperature Characteristics



MULTILAYER CERAMIC CAPACITORS

EPOXY COATED AXIAL TYPE

11.Temperature Characteristics

